

RELOADING ALLOYS SPECIFICATIONS

Alloys Code	Name	Composition %			Hardness Brinell	weight lbs	Ingot size, inch			Net weight per bundle, lb
		Tin	Antimony	Lead			H	W	L	
EA-HB	Hardball	2	6	92	16	7.40	1.75	2	9	1909.20
EA-LT	Linotype	4	12	84	22	7.00	1.75	2	9	1806.00
EA 20	1:20	4.7	0	95.3	10	7.45	1.75	2	9	1922.10
EA 30	1:30	3.2	0	96.8	8	7.65	1.75	2	9	1973.70
EA- PL	Pure lead	0	0	99.96	6	7.70	1.75	2	9	1986.60
EA-PT	Pure Tin	99.95	0	0		1.00	0.63	1	9	258.00